

The braided suture is made up of multifilament yarns. A multifilament yarn is a bundle of individual filaments which are integrated to form a single unit, that is, an individual multifilament yarn. The braided suture has a first and second set of these multifilament yarns in a braided construction. Each of the filaments of the first set of yarns is composed of a first fiber-forming material. Similarly, each of the filaments of the second set of yarns is composed of a second fiber-forming material.

The importance of the construction of the first and second set of yarns cannot be diminished. The braided construction is not accurately characterized by simply referring to a suture with filaments of dissimilar fiber-forming materials in a braided construction. Rather, filaments of a first fiber-forming material must be bundled to prepare a first set of multifilament yarns, and filaments of the second fiber-forming material must also be bundled to prepared the second set of multifilament yarns.

Once an understanding of the composition and construction of each set of first and second yarns is achieved, the importance of a further characterization of the braid construction can now be understood and appreciated. One yarn from the first set of yarns is in direct intertwining contact with a yarn from the second set of yarns. This limitation does not simply mean that the dissimilar filaments are fabricated into a braided construction, that is, dissimilar filaments are in "intertwining contact". Rather it is a multifilament yarn which is in direct intertwining contact with another multifilament yarn. Again, it is important to emphasize here that the multifilament yarns are integrated bundles of individual filaments, and it is this integrated bundle of filaments of a first fiber-forming material which is in direct intertwining

contact with another integrated bundle of individual filaments of a second fiber-forming material.

One way to accurately characterize the braided suture of this invention is to refer to it as a structured mechanical blend of dissimilar fiber-forming materials. The fiber-forming materials are first arranged into integrated bundles to form multifilament yarns and then these multifilament yarns are further arranged so that at least one yarn from the first set of yarns directly intertwines with a multifilament yarn from the second set of yarns. This can be contrasted with a random, braided construction where filaments of dissimilar fiber-forming materials are randomly braided with one another to form a braided suture.

The heterogeneous braids of this invention exhibit truly outstanding and surprising properties. The integrity of the braid and therefore its properties is due entirely to the mechanical interlocking or weaving of the individual multifilament yarns (see the specification at page 4, lines 30-33). In the preferred embodiment, each yarn from the first set of multifilament yarns is in direct intertwining contact with a yarn of the second set to achieve the maximum degree of mechanical blending of the dissimilar multifilament yarns (see the specification at page 6, lines 28-31, and claim 15). In this way, yarn compatibility can be further enhanced and the overall physical and biological properties of the heterogeneous braid can be further improved as well.

What is truly surprising with respect to the claimed heterogeneous braid construction is that certain bulk properties of the claimed braid are better than what one skilled in the art would expect. A skilled artisan would expect the properties of the braid to simply follow the "Rule of Mixtures", where the bulk property